

CAB-O-SIL® EH-5 Fumed Silica



CAB-O-SIL EH-5 fumed silica is a very high surface fumed silica which can increase the viscosity of liquid systems and provide significant reinforcement of silicone and organic rubbers.

All untreated fumed silicas are characterized by:

- High purity
- Aggregated structure
- Submicron particle size
- Low bulk density
- Hydrophilic surface chemistry

Application Information

Rheology Control for Coatings, Adhesive and other Liquid Systems

CAB-O-SIL EH-5 fumed silica can be used to provide thickening, thixotropic (shear-thinning), and anti-settling behavior in liquid systems. Very high shear dispersion equipment is required to realize the full benefits of this product. For clear coatings and other systems, very well dispersed CAB-O-SIL EH-5 fumed silica provides greater transparency than lower surface area fumed silicas. Untreated fumed silicas are most efficient in non-polar to medium polar systems for building viscosity and improving sag-resistance. For more polar systems, treated fumed silicas may be more efficient.

Reinforcement of Silicone and Organic Rubber

CAB-O-SIL EH-5 fumed silica can be used for reinforcement of silicone rubber and can be used to reinforce organic rubbers. It imparts good increase in hardness, tensile and elongation. For clear silicone rubber applications, well-dispersed CAB-O-SIL EH-5 fumed silica provides excellent transparency.

Packaging Options

CAB-O-SIL EH-5 fumed silica is packaged in multi-wall Kraft paper bags and flexible intermediate bulk containers (FIBCs). In North America it is available in poly-shrouded units containing 18 x 10 lb. paper bags (180 lb. net weight) and in 250 lb. FIBCs. In Europe it is available in poly-shrouded units containing 18 x 10 kg paper bags (180 kg net weight) and in 150 kg FIBCs.

CAB-O-SIL® EH-5 Fumed Silica

Material Safety Data Sheet

A Material Safety Data Sheet for this product may be obtained from your local Cabot representative or can be downloaded from our website at cabotcorp.com.

Product Sales Specifications

Sales specifications for this product may be obtained from your local Cabot representative.



NORTH AMERICA

Cabot Corporation Business
and Technical Center
157 Concord Road
Billerica, MA 01821-7001
USA

TEL +1 800 462 2313
FAX +1 978 670 7035

SOUTH AMERICA

Cabot Latin American
Division
Rue do Paraíso, 148 -
5º andar
04103-000, São Paulo,
SP BRAZIL

TEL +55 11 2144 6400
FAX +55 11 3253 0051

EUROPE

Cabot Specialty Chemicals
Interleuvenlaan 15 i
3001 Leuven,
BELGIUM

TEL +32 16 39 24 31
TEL +32 16 39 25 68
FAX +32 16 39 24 44

MIDDLE EAST/AFRICA

Cabot Specialty Chemicals
Jebel Ali Free Zone
LOB 15, Office 424
Dubai

UNITED ARAB EMIRATES
TEL +971 4 8871 800
FAX +971 4 8871 801

ASIA PACIFIC

Cabot China Ltd.
558 Shuangbai Road
Shanghai 201108,
CHINA

TEL +86 21 5175 8800
FAX +86 21 6434 5532

JAPAN

Cabot Specialty Chemicals, Inc.
Sumitomo Chiba-Daimon Bldg. 3 F
2-5-5 Shiba Daimon,
Minato-ku, Tokyo 105-0012,
JAPAN

TEL +81 3 6820 0255
FAX +81 3 5425 4500

The data and conclusions contained herein are based on work believed to be reliable, however, Cabot cannot and does not guarantee that similar results and/or conclusions will be obtained by others. This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and CABOT DISCLAIMS ALL WARRANTIES EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AS TO (i) SUCH INFORMATION, (ii) ANY PRODUCT OR (iii) INTELLECTUAL PROPERTY INFRINGEMENT. In no event is Cabot responsible for, and Cabot does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.